

### Paint Testing Report

**Manufacturer:**

Sherwin Williams  
101 Prospect Ave. NW  
Cleveland, OH 44115-1075

**Testing Laboratory:**

U. S. Army CERL  
ATTN: CECER-CF-M  
P. O. Box 9005  
Champaign, IL 61826-9005

**Product Designation:**

Epoxy Mastic Aluminum II

**Sample Designation:**

Lab report 95L185

**Specification:** CID A-A-3127

**Date:** 18 OCT 95

<b>Analysis:</b>	<b>Min</b>	<b>Max</b>	<b>Result</b>	<b>Pass</b>
Condition in container			OK	YES
Application properties, spray:			OK	YES
Application properties, roller:			OK	YES
Prohibited Materials Lead,		0.06	ND	YES
Prohibited Materials (See Spec.)		0.1	ND	YES
Dry Hard Time (Hours)		16	OK	YES
Pot Life (Hours )	3		>3	YES
Intercoat Adhesion			OK	YES
VOC as applied (g/L)		350	173	YES
<b>Accelerated Corrosion Resistance (4032 Hours)</b>				
Blistering at Scribe at 2688 hours		1	0	YES
Blistering at Scribe at 3360 hours		4	0	YES
Blistering at Scribe (Average Rating)	6.5		10.0	YES
Other blistering on panels		None	None	YES
Rust rating, ASTM D 610 (Average Rating)	9.0		9.0	YES
Rust Undercutting (Max.)	6.0		6.0	YES
Rust Undercutting (Average Rating)	6.0		6.3	YES
Composite of averages (Rust + Blister + Undercut)	23.0		25.3	YES

Sample meets all specification requirements? YES ☒ NO ☐

Remarks:

Signature: